



50° Gloss Black Lacquer 91-10020

320 Paterson Plank Road
 Carlsadt, NJ 07072
 Tel 800-426-0496
 201-933-1000
 Fax 201-933-3646

Product Description

EPA compliant nitrocellulose lacquer

Recommended Uses

Fine finishing of wood furniture, architectural woodwork, musical instruments, picture frames and other decorative accessories.

Benefits

- Excellent build.
- No reduction - ready to spray.
- Very fast drying.
- High solids by weight and volume.
- High spreading rate.
- Easy to repair.
- Compliant with state and federal EPA standards.

Surface Preparation

Wood surfaces must be sanded smooth with the grain, and surface blemishes must be corrected. All surfaces must be free from grease and other foreign matter, and completely dry prior to coating.

Application

Reduction

Can be applied 'as is'.

Application

Conventional spray

Drying Time

To touch: 10 - 15 minutes. To handle: 25 - 35 minutes. To woof 1 hour. To pack: overnight.

Safety

Consult MSDS sheets 8, label warnings

continued



50° Gloss Black Lacquer 91-10020

320 Paterson Plank Road
Carlsadt, NJ 07072
Tel 800-426-0496
201-933-1000
Fax 201-933-3646

Specifications

Color	Black
Gloss	60° Angular - 15 ± 2
Mixed Viscosity	45.-± 2 seconds #2 Zahn Cup 0 77° F
Density	7.87 lbs/gal
Solids by Weight	37.34%
Solids by Volume	26.90%
VOC	4.93 lbs/gal 5.91 gms/lit
Coverage	430 sq ft/gal @ one mil dry film thickness
Recommended Dry Film Thickness	1.5 - 2 mils
Storage Conditions	Store in a tightly closed container at room temperature (64 - 75° 6), and protect from moisture and foreign material. For best results, bring point to room temperature (776) prior to use.