



# 50° Gloss Black Lacquer 91-10006

320 Paterson Plank Road

Carlsadt, NJ 07072

Tel 800-426-0496

201-933-1000

Fax 201-933-3646

**Specifications**

<b>Color</b>	White
<b>Gloss</b>	60° Angular Gloss - 50 ± 2
<b>Mixed Viscosity</b>	40.± 2 seconds #2 Zahn Cup @ 77° F
<b>Density</b>	8.56 lbs/gal
<b>Solids by Weight</b>	42%
<b>Solids by Volume</b>	26.56%
<b>VOC</b>	4.96 lbs/gal 5.95 gms/lit
<b>Coverage</b>	425 sq ft/gal @ one mil dry film thickness
<b>Recommended Dry Film Thickness</b>	1.5 - 2 mils
<b>Storage Conditions</b>	Store in a tightly closed container at room temperature (64 - 75° F), and protect from moisture and foreign material. For best results, bring point to room temperature (77F) prior to use.