



320 Paterson Plank Road  
 Carlsadt, NJ 07072  
 Tel 800-426-0496  
 201-933-1000  
 Fax 201-933-3646

# 15° Gloss White Lacquer 91-10011

**Specifications**

<b>Color</b>	White
<b>Gloss</b>	60° Angular Gloss - 50 ± 2
<b>Mixed Viscosity</b>	40.-± 2 seconds #2 Zahn Cup @ 77° F
<b>Density</b>	8.48 lbs/gal
<b>Solids by Weight</b>	42%
<b>Solids by Volume</b>	24.50%
<b>VOC</b>	4.92 lbs/gal 5.91 gms/lit
<b>Coverage</b>	384 sq ft/gal @ one mil dry film thickness
<b>Recommended Dry Film Thickness</b>	2 - 3 mils
<b>Storage Conditions</b>	Store in a tightly closed container at room temperature (55 - 90° F), and protect from moisture and foreign material.
<b>Recommended Primer</b>	M5378 White sanding lacquer undercoat